

VEZIVO	MOTORNO OLJE	DIESEL	NEOSVINČENI BENZIN(S95)	IPA	ACETON	OSMOZNA VODA	H2SO4 SOLUTION 10% MASS	H2SO4 SOLUTION 36% MASS	NAOH SOLUTION 5% MASS	HCL SOLUTION 10% MASS	DEBELINA SUHEGA FILMA (µm)
ACRYL 170	0	1	2	5	5	0	0	0	0	0	65-70
ACRYL 172	0	2	5	5	3	0	2	0	2	0	65-70
ACRYL 173G	0	0	5	5	3	0	0	0	0	0	35-45
ACRYL 173M	0	1	5	5	4	0	0	0	1	0	35-45
EPO 600-G	0	0	0	0	5	0	3	0	1	0	90-100
EPO 680	0	0	0	0	5	0	0	0	0	0	80-85
SINT 300	0	0	5	5	5	0	0	4	0	0	60-65
SINT 470	0	0	3	5	5	0	0	4	0	0	60-65
SIN 700-G	0	0	1	4	4	0	0	4	0	0	30-40
SINT 700-S	0	0	3	5	0	0	0	4	0	0	50-60
SINT 702-S	0	0	4	4	4	0	0	4	0	0	50-60
SINT 742G	0	0	3	5	3	1	0	4	0	1	35-45
SINT 744-G	0	0	5	5	5	0	0	0	0	0	35-40
SINT 744-M	0	0	5	4	5	0	0	0	0	0	30-35
SINT 790	0	0	2	2	0	0	0	5	2	0	50-60
PUR 800-G	0	0	3	3	5	0	0	0	0	0	50-60
PUR 800-S	0	0	3	3	5	0	0	0	0	0	50-60
PUR 800-M	0	0	3	3	5	0	0	1	0	0	60-70
PUR 840-G	0	0	3	3	3	0	0	1	0	0	40-50
PUR 840-M	0	0	3	3	4	0	0	2	0	0	40-50
PUR 840-S	0	0	5	3	4	0	0	0	0	0	40-50
PUR 844-G	0	0	0	2	2	0	0	0	0	0	150
PUR 870	0	0	3	3	4	0	0	0	0	0	60-70
PUR 882	0	0	1	-	-	-	0	-	0	0	25-35
PUR 890	0	0	1	2	3	0	0	4	2	0	60-70
PRO 84X-G	0	0	0	1	0	0	0	0	0	0	60-70
ACRY-PUR 902-G	0	0	3	3	4	0	0	0	0	0	50-60
ACRY-PUR 901-G	0	0	2	2	1	0	0	0	0	0	60-70
ACRY-PUR 901-M	0	0	4	3	4	0	0	1	0	0	50-60

KEY
(ISO 4628-1)

STOPNJA Intenzivnost spremembe

- 0  Nespremenjeno, neznatne spremembe.
1  Zelo rahlo, komaj zaznana sprememba.
2  Rahlo. Jasno zaznavna sprememba.

- 3  Zmerno. Sprememba jasno zaznavna.
4  Občutno. Izrazita sprememba.
5  Zelo intenzivna sprememba.