



## POLIFOND 775

<b>1) Kodal Code:</b> 175.001.001	<b>2) Opis \ Description:</b> 2k Pur brezbarvni temeljni lak, visoke transparentnosti in polnilnosti za lesena tla 2k PUR clear base coat, good built and high transparency for wooden floors
--------------------------------------	---

<b>3) Glavne lastnosti \ Main characteristics of the product:</b>	
<ul style="list-style-type: none"> <li>Transparentnost \ Transparency</li> <li>Dobra polnilnost \ Good built</li> <li>Izjemno razlivanje \ Excellent floating</li> </ul>	<ul style="list-style-type: none"> <li>Odlična elastičnost \ Excellent flexibility</li> <li>Dobra svetlobna odpornost \ Good light fastness</li> </ul>

<b>4) Področja uporabe \ Range of use:</b>
Brezbarvni 2k PUR temeljni lak primeren za ravne površine kot so, parket, stopnice in lesena tla. Vsebuje UV filtre! Primerno tudi za zunanjo zaščito! It's a clear 2K PUR base coat, suitable for layering wooden floors, parquet and steps.. It contains UV absorber in the formula. It's also fit for outdoor woodwork.

<b>5) Nanos \ Way of use:</b>
običajna brizgalna pištola Conventional spray gun

<b>6) Karakteristike \ Physycal-chemical characteristics (20 °C):</b>	
Izgled \ Appearance	: nizko viskozna tekočina \ Low viscosity liquid
Barva \ Color	: blede rumena \ pale yellow
Vsebnost suhih snovi \ Solid content (peso \ weight, ± 2%)	: 45
HOS \ VOC (peso \ weight, ± 2%)	: 55
Specifična teža \ Specific gravity (Kg./dm <sup>3</sup> , ± 2%)	: 0,980 (parte A \ pale yellow)
Viskoznost v embalaži \ Vx in can (DIN 4, sec., ± 5)	: 30 sec.
Viskoznost pri nanosu \ Vx at the use (DIN 4, sec., ± 3)	: 18

<b>7) Komponenta B in razmerje \ Curing agent and ratio:</b>	<b>% teža \ weight</b>	<b>% volumen</b>
B-775	50	50
Vsebnost suhih snovi komp. B / solid content part: 33 (+ 2%)		

<b>8) Lastnosti nanosa \ Application characteristics (20 °C):</b>	
Poraba \ Yeald, each layer (gr./m <sup>2</sup> )	: 120-160
Št. nanosov \ Suggested layers	: 2-3 \ up to 2-3 layers
Čas med nanosi \ Time between the layers	: 60-90 min.

<b>9) Sušenje \ Drying (20 °C, R.U. 45-65%):</b>			
Odprti čas:	: >3 ure \ hours	Lakiranje čezenj \ Overlayer ability	: čez noč \ after overnight
Prašno suho \ Dust free	: 30 min.	Zlaganje \ Stack ability	: 24 ur \ hours
Suho na dotik \ Touch free	: 60 min.	Pakiranje \ Packable	: 48 ur \ hours
Sušenje \ Drying	: 24 ur \ hours (35°C)	Brušenje \ Sand ability	: 24 ur \ hours



<b>10) Sušenje v tunelu \ Drying in tunnel (U.R. 45-65.%):</b>	Temperat.	Čas \ Time
Flash off	30 °C	15 min.
Laminarni zrak \ Laminar air		
Hlajenje \ Cooling		

<b>11) Mešalno razmerje \ Mixture preparation steps:</b>	<b>% teža \ weight</b>	<b>% volumen</b>
POLIFOND 775	= 100	= 100,0
B-775	= 50	= 50,0
MAX THINNER 890	= 10-25	= 10-25,0
----- dobro premešari \ Mix well -----		

<b>12) Alternativni trdilci, pospeševalci, razrečila \ Alternative curing agents, accelerators, &amp; thinners:</b>

<b>13) priprava podlage \ Substrate preparation:</b>
Obrusiti podlago z brusnim papirejem granulacije 180-220. Za obarvanje lesa uporabite UNICOLOR ali ACQUACOLOR lužila oz. Alternativa SOLVASHADE in ACQUASHADE. <i>Sand the timber with 180-220 abrasive paper. To tone the wood, use UNICOLOR or ACQUACOLOR dyes series, or in alternative the SOLVASHADE or ACQUASHADE stain series (mocopigmented based).</i>

<b>14) Nasveti \ Tips &amp; tricks :</b>
Pri visokih temperaturah dodajte k razredčilu 5% ADDITIVO RITARDANTE AC. <i>In case of hot environmental temperatures, add to the thinner the 5% of ADDITIVO RITARDANTE AC</i>

<b>15) Embalaža \ Packaging:</b>
<b>POLIFOND 775</b> : L.25 - L. 5
<b>B-775</b> : L.12,5 - L.2,5

<b>16) Skladiščenje \ Storing:</b>
Ta proizvod s pripadajočimi trdilci in razredčili, če so skladiščeni v hladnem okolju v originalno zaprti embalaži nimajo roka uporabe. Po odprtju pločevink, tesno zaprite embalažo! <i>This product and its curing agent do not have any expiring date if stored in a cool environment in their original and sealed containers. After the use, close the containers.</i>

Le informazioni contenute in questa scheda si basano sulle nostre migliori attuali conoscenze. Non devono perciò intendersi come garanzia di proprietà specifiche o assunzione di responsabilità. Per ogni eventuale argomento non trattato in questa scheda tecnica si consiglia di consultare il nostro laboratorio. Tutti i cicli e prodotti proposti si intendono applicati su supporti dimensionalmente stabili, con legni in condizione di preparazione ottimale (stagionatura, umidità, ecc.). La presente scheda sostituisce tutte le eventuali precedenti.

*The information reported in these sheets are based on our best knowledge's. They cannot be considered as warranty or undertaking of responsibilities. For any argument not treated in this technical data sheet, call our technical support. All the mentioned painting cycles are intended for dimensional stable board, using timbers prepared in the optimal conditions (weathering, humidity, etc.). This sheet replaces all the previous ones.*